



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>C12N 15/52, C12P 7/62, C12N 9/00 //</b> <b>(C12N 1/21, 5:14)</b>	<b>A1</b>	(11) International Publication Number: <b>WO 98/04713</b> (43) International Publication Date: <b>5 February 1998 (05.02.98)</b>
<p>(21) International Application Number: <b>PCT/US97/13301</b></p> <p>(22) International Filing Date: <b>25 July 1997 (25.07.97)</b></p> <p>(30) Priority Data: <b>687,806</b> <b>26 July 1996 (26.07.96)</b> <b>US</b></p> <p>(71) Applicant: <b>MASSACHUSETTS INSTITUTE OF TECHNOLOGY [US/US]; 77 Massachusetts Avenue, Cambridge, MA 02139 (US).</b></p> <p>(72) Inventors: <b>SNELL, Kristi, D.; 8 Walnut Street, Belmont, MA 02178 (US). HOGAN, Scott, A.; Apartment 106, 2354 Golfview Drive, Troy, MI 48084 (US). SIM, Sang, Jun; Kunyoung Apartment 102-1608, Sangbong-dong, Jungnang-gu, Seoul 131-220 (KR). SINSKEY, Anthony, J.; 285 Commonwealth Avenue, Boston, MA 02115 (US). RHA, Chokyun; 285 Commonwealth Avenue, Boston, MA 02115 (US).</b></p> <p>(74) Agent: <b>PABST, Patrea, L.; Amall Golden &amp; Gregory, LLP, 2800 One Atlantic Center, 1201 West Peachtree Street, Atlanta, GA 30309-3450 (US).</b></p>		<p>(81) Designated States: <b>AU, CA, JP, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</b></p> <p><b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: <b>METHOD FOR CONTROLLING MOLECULAR WEIGHT OF POLYHYDROXYALKANOATES</b></p> <p>(57) Abstract</p> <p>A method has been developed for control of molecular weight and molecular weight dispersity during production of polyhydroxyalkanoates in genetically engineered organism by control of the level and time of expression of one or more PHA synthases in the organisms. The method was demonstrated by constructing a synthetic operon for PHA production in <i>E. coli</i> in which the level of PHA synthase activity could be tightly controlled by placement of the synthase behind an inducible promoter. Modulation of the total level of PHA synthase activity in the host cell by varying the concentration of the inducer, isopropyl <math>\beta</math>-D-thiogalactoside (IPTG), was found to effect the molecular weight of the polymer produced in the cell. Specifically, high concentrations of synthase activity were found to yield polymers of low molecular weight while low concentrations of synthase activity yielded polymers of higher molecular weight. Polymer molecular weight dispersity is also proportional to the amount of synthase activity, with less dispersity in polyhydroxyalkanoate compositions produced in expression systems with an initial burst of synthase activity, and higher levels of molecular weight dispersity in polyhydroxyalkanoate compositions produced in expression systems with the levels of synthase activity varied during synthesis of the polyhydroxyalkanoate.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## METHOD FOR CONTROLLING MOLECULAR WEIGHT OF POLYHYDROXYALKANOATES


### Background of the Invention

This invention relates to controlling the molecular weight and  
5 distribution of polyhydroxyalkanoates produced *in vivo* in a host cell by  
genetically engineering the amount of polyhydroxyalkanoate polymerase  
which is expressed in the host cell.

The United States government has certain rights in this invention  
by virtue of National Institutes of Health grant NIH-1-RO1-GM49171-  
10 01A1 to JoAnne Stubbe, A.J. Sinskey, and S. Masamune

Polyhydroxyalkanoates (PHAs) are a class of polyesters that are  
produced by many organisms as an intracellular energy reserve during  
nutrient deprivation (Anderson and Dawes, Microbiological Reviews,  
1990, 54, 450-472.; Poirier et al., Bio/Technology 1995, 13, 142-150.).  
15 Since PHAs are naturally biodegradable, they are considered an attractive  
alternative to conventional plastics in terms of reducing solid waste.  
*Alcaligenes eutrophus* is an example of an organism that produces  
abundant granules of the polyester during nutrient limiting conditions.  
The PHA biosynthetic pathway in *A. eutrophus* consists of three enzymes,  
20 a thiolase, a reductase, and a synthase. Two acetyl-CoA units are  
condensed by  $\beta$ -ketothiolase to form acetoacetyl-CoA, which is  
stereospecifically reduced by an NADPH dependent reductase to form 3-  
D-hydroxybutyryl-CoA (HBCoA). PHA synthase catalyzes the  
polymerization of HBCoA monomer units to form polymer.

-2-



- The operon containing the PHA biosynthetic genes from *A. eutrophus* has been cloned, allowing its expression in *Escherichia coli* (Peoples and Sinskey, J. Biol. Chem. 1989, 264, 15298-15303; J. Biol. Chem. 1989, 264, 15293-15297; Slater et al., J. Bacteriol. 1988, 170, 4431-4436; Schubert et al., J. Bacteriol. 1988, 170, 5837-5847). Wild-type *E. coli* is itself capable of producing small amounts of a form of polyhydroxybutyrate (PHB) that is found complexed to the cell membranes (Huang and Reusch, J. Bacteriol. 1993, 177, 486-490), however the abundant granules found in other microorganisms such as *A. eutrophus* during nutrient limiting conditions are not present in *E. coli*.
- Insertion of a plasmid-borne copy of the PHA biosynthetic operon from *A. eutrophus* enables *E. coli* to produce PHB granules visible by transmission electron microscopy (Lee et al., 1994a). Considerable attention has been devoted to the fermentation of genetically engineered *E. coli* PHB producers (Lee et al., 1994a and Lee, et al., Journal of Biotechnology 1994, 32, 203-211; Kim et al., Biotechnology Letters, 1992, 14, 811-818.; Kidwell et al., Applied and Environmental Microbiology 1995, 61, 1391-1398), however little effort has been made to characterize the size of the polymer produced or to develop methods to control polymer molecular weight. As reviewed by Gilbert, "Molecular Weight Distributions in Free-Radical Polymerizations: Their Cause and

Cure" Trends in Polymer Science 1995, 3, 222-226, the average molecular weight and the molecular weight distribution are some of the most important determinants of the properties of a polymer.

- Gerngross and Martin, Proc. Natl. Acad. Sci. USA 92:6279-6283 (July 1995), describe a method for increasing the molecular mass of poly[(R)-(-)-3-hydroxybutyrate] (PHB) granules by exposing purified PHA synthase to (R)-3-hydroxybutyryl coenzyme A, and determined that the molecular mass of the polymer is dependent on the initial PHA synthase concentration in a cell free, *in vitro* system wherein specific substrate is added. While this is an interesting research observation, it provides little basis on which commercial synthesis of polymer of defined molecular weight can be produced in a bacterial system where many other enzymes and substrates are present. The substrate needed for *in vitro* polymerization, D-3-hydroxybutyrylCoA, is only commercially available as a mixture of D and L diastereoisomers. The current cost of D,L-3-hydroxybutyrylCoA from Sigma Chemical Company, St. Louis, MO, is \$187.55 for 25 milligrams of material.

- Huisman, in his Ph.D. thesis entitled "Synthesis of poly(3-hydroxyalkanoates) by mutant and recombinant strains of *Pseudomonas putida*" submitted to the University of Groningen, The Netherlands, 1991, and Huisman, et al., Appl. Microbiol. Biotechnol. 38:1-5 (1992), analyzed the poly(3-hydroxyalkanoates) produced in mutants defective in PHA metabolism. Comparisons of molecular weights and quantities of polymer were made based on the substrate provided to the mutant. It was postulated that, in addition to substrate, the polymerase played a role in determining the molecular weight of the resulting polymer. Average PHA molecular weight was theorized to be inversely proportional to polymerase activity, but the exact role and its relationship to substrate availability in final product characteristics were not determined. Moreover, the studies were conducted using plasmid-based expression of PHA synthase genes from one strain, *Pseudomonas oleovorans*, in a host of a different strain, *P. putida*, a system that does not necessarily guarantee expression. No

-4-

enzyme activity data was provided to support claims of expression in this heterologous system. The strain is also capable of degrading polymer. Indeed, the results suggest degradation by depolymerases, not control of synthase activity, since polymer yields decrease with decreases in molecular weight.

Although a correlation between molecular weight of the resulting polymer and concentration of PHA synthase has been suggested, many factors, including substrate availability, clearly play a role.

It is therefore an object of this invention to provide a method for controlling polymer molecular weight and molecular weight dispersity.

### Summary of the Invention

A method has been developed for control of molecular weight and molecular weight dispersity during production of polyhydroxyalkanoates in genetically engineered organisms by control of the level and time of expression of one or more PHA synthases in the organisms. The method was demonstrated by constructing a synthetic operon for PHA production in *E. coli* in which the level of PHA synthase activity could be tightly controlled by placement of the synthase behind an inducible promoter. Modulation of the total level of PHA synthase activity in the host cell by varying the concentration of the inducer, isopropyl  $\beta$ -D-thiogalactoside (IPTG), was found to effect the molecular weight of the polymer produced in the cell. Specifically, high concentrations of synthase activity were found to yield polymers of low molecular weight while low concentrations of synthase activity yielded polymers of higher molecular weight. Polymer molecular weight dispersity can be controlled by modulating the synthase activity during the polymer synthesis reaction. For example, low synthase activity at the beginning of the fermentation yields high molecular weight polymer of low molecular weight dispersity; increasing synthase activity during fermentation results in synthesis of lower molecular weight polymer, thereby increasing the molecular weight dispersity of the polymer produced during the fermentation. Examples

demonstrate the synthesis of polymers having a range of molecular weights between  $4 \times 10^6$  and  $7.8 \times 10^5$ , and defined molecular weight distributions (polydispersity indices from 1.02 and 2.81).

### Brief Description of the Drawings

5            Figures 1A, 1B, and 1C are graphs of dry cell weight (DCW), PHB concentration (PHB), and glucose concentration during 13 L fermentations of strains DH5 $\alpha$ /pAet41 (Figure 1A), DH5 $\alpha$ /pSP2 with 0.4 mM IPTG induction (Figure 1B), and DH5 $\alpha$ /pSP2 with 5 mM IPTG induction (Figure 1C).

10           Figure 2 is a graph of enzyme activities (specific activity, units/mg, time, hour) of the synthase in soluble lysate fractions of strains DH5 $\alpha$ /pAet41 (triangles), DH5 $\alpha$ /pSP2 with 0.4 mM IPTG induction (circle), and DH5 $\alpha$ /pSP2 with 5 mM IPTG induction (solid circle).

15           Figure 3A is a graph of synthase activity (specific activity, units/mg over time, hour) for crude lysates of strains DH5 $\alpha$ /pAet41 (triangle), DH5 $\alpha$ /pSP2 with 0.4 mM IPTG induction (circle), and DH5 $\alpha$ /pSP2 with 5 mM IPTG induction (solid circle). The crude lysate is defined as the lysate fraction containing both soluble and insoluble enzyme fractions.

20           Figure 3B is a graph illustrating multi-angle light scattering molecular weight analysis of polymer isolated from strains DH5 $\alpha$ /pAet41 (triangle), DH5 $\alpha$ /pSP2 with 0.4 mM IPTG induction (circles), and DH5 $\alpha$ /pSP2 with 5 mM IPTG induction (solid circles).

25           Figure 4 is a graph of the activity of the reductase (specific activity, units/mg, over time, hours) in soluble lysate fractions of strains DH5 $\alpha$ /pAet41 (triangle), DH5 $\alpha$ /pSP2 with 0.4 mM IPTG induction (circle), and DH5 $\alpha$ /pSP2 with 5 mM IPTG induction (solid circle).

30           Figure 5 is a graph of the activity of the thiolase in soluble lysate fractions of strains DH5 $\alpha$ /pAet41 (triangle), DH5 $\alpha$ /pSP2 with 0.4 mM IPTG induction (circles), and DH5 $\alpha$ /pSP2 with 5 mM IPTG induction (solid circles).

-6-

Figure 6A is a graph of the polydispersity index ( $M_w/M_n$ ) over time (hours) of polymer isolated from strains DH5 $\alpha$ /pAeT41 (triangles), DH5 $\alpha$ /pSP2 with 0.4 mM IPTG induction (circles), and DH5 $\alpha$ /pSP2 with 5mM IPTG induction (solid circles), as calculated by gel permeation chromatography in line with light scattering. Figures 6B and 6C are raw gel permeation chromatograms performed without light scattering of polymer isolated from strain DH5 $\alpha$ /pSP2 induced with 0.4 mM IPTG (Figure 6B) and polymer isolated from strain DH5 $\alpha$ /pSP2 induced with 5 mM IPTG (Figure 6C).

Figures 7A and 7B are schematics of the construction of plasmid pSP2.

### Detailed Description of the Invention

The polyhydroxyalkanoates (PHAs) detected in bacteria can be divided into two main groups, those containing short chain monomer units (3-5 carbon atoms) and those containing medium chain monomer units (6-14 carbon atoms) (Lee, S. Y. *Biotechnology and Bioengineering* 49, 1-14, 1996). The synthase enzymes are generally divided into three classes: Type I, such as *A. eutrophus*, that synthesize polymer with short chain monomer units; Type II, such as *Pseudomonas oleovorans*, that synthesize polymer containing medium chain monomer units; and Type III, such as *Chromatium vinosum*, that require the expression of a second gene *phaE* for synthase activity and predominantly synthesize short chain polymers. There has been a synthase found in the type III group from *T. pfennigii* that synthesizes a copolymer composed of short and medium chain length monomer units (Poirier et al., *Bio/Technology* 13, 142-150, 1996).

Short chain monomer units that are recognized as substrates by the short chain PHA synthases include 3, 4, and 5-hydroxyacyl CoAs [Lee, S. Y. *Biotechnology and Bioengineering* 49, 1-14, 1996]. In general, the presence of a thiolase and reductase is needed to make polymer in short chain production systems. For example, 3-hydroxybutyrylCoA is formed from acetylCoA via 3-ketothiolase and acetoacetyl reductase. Other short



-7-

chain monomer units can be formed by adding alkanolic acids or hydroxyalkanoic acids to the bacterial growth medium. Alkanolic acids, such as propionic acid, are converted to acyl CoAs, via a CoA synthase, which are subsequently converted to hydroxyacylCoA's via a thiolase and reductase (Poirier et al., Bio/Technology 13, 142-150, 1995). However, hydroxyalkanoic acids are converted to hydroxyacylCoAs by the bacteria without the need of thiolase or reductase enzymes.

Monomer units of medium chain length PHAs are derived either from alkanolic acids added to the bacterial growth medium or from the fatty acid biosynthetic and  $\beta$ -oxidation pathways when the bacteria are grown on simple sugars. *P. oleovorans* is an exception in that it has not been found to produce PHAs when grown on simple sugars (Poirier et al., Bio/Technology 13, 142-150, 1995). Acyl CoAs, formed from the alkanolic acid via an acyl CoA synthase, are converted to hydroxyacyl CoAs by the  $\beta$ -oxidation pathway (Poirier et al., Bio/Technology 13, 142-50, 1995). Thus, medium chain length polymer production systems do not need the thiolase and reductase, however, they do require the presence of  $\beta$ -oxidation and fatty acid biosynthetic pathway enzymes.

Molecular weight control by controlling synthase activity applies to all classes of polymers, not just PHB, as well as all classes of synthases.

### PHA Synthases

Many different PHA synthases are known, characterized and the encoding DNA is sequenced. These are generally derived from natural sources, but can include synthases with conservative substitutions in the amino acid sequences.

References for sequences of known synthases include:

- Paracoccus denitrificans*: Ueda, et al., Journal of Bacteriology 1986, 178, 774-779; *A. eutrophus*: Peoples, et al., J. Biol. Chem. 1989, 264, 15293-15297 (Genbank accession number JO5003); *Acinetobacter* sp.: Schembri, et al., FEMS Microbiol. Lett. 1994, 118, 145-152; *Chromatium vinosum*: Liebergesell, et al., Eur. J. Biochem. 1992, 209, 135-150; *M. extorquens*: Valentin, et al., Appl. Microbiol. Biotechnol.

-8-

- 1993, 39, 309-317; *Pseudomonas aeruginosa* 1 and 2: Timm, et al. Eur. J. Biochem., 1992, 209, 15-30; *Pseudomonas oleovorans* 1 and 2: Huisman, J. Biol. Chem., 1991, 266, 2191-2198; *Rhodococcus ruber*: Pieper, et al., FEMS Microbiol. Lett., 1992, 96, 73-80; *R. sphaeroides*:  
5 Hustede, et al., Biotechnol. Lett., 1993, 15, 709-714; *Thiocystis violacea*: Liebergesell, et al., 1993, 38, 493-501.

#### Thiolases and Reductases

- A. eutrophus* thiolase and reductase are described by Peoples and Sinskey, J. Biol. Chem., 264, 15293-15297 (1989) and available from  
10 Genbank under the accession number JO4987.

#### Depolymerases

- In *E. coli* it is not necessary to inactivate the depolymerase since there is no known depolymerase and degradation has not been observed. However, in other host strains where a functional depolymerase exists, it  
15 would be desirable to eliminate the depolymerase so that the polymer product does not degrade. A depolymerase can be inactivated by mutagenesis of the host strain.

#### Expression Vectors

- The gene encoding the synthase, as well as any other enzymes  
20 such as the reductase and thiolase, can be inserted into an appropriate vector for expression in a host system. In the preferred embodiment, the vector is a plasmid expressable in a bacteria such as *Escherichia coli*. Suitable plasmids can be obtained from commercial sources including the American Type Culture Collection, Rockville, MD. Other commercial  
25 sources for expression vectors include Pharmacia Biotech Inc., Piscataway, NJ; Clontech Laboratories, Inc., Palo Alto, California; Promega, Madison, WI.

- In the preferred embodiment, expression of the synthase is under the control of an inducible promoter, as demonstrated by the following  
30 examples. Promoters that can be utilized to regulate the expression of PHA synthase in bacterial hosts include, but are not limited to, an IPTG inducible promoter such as the *lac*, *trc*, or *tac* promoters; a pH regulated

promoter regulated by pH (Tolentino et al, Biotechnology Letters, 14, 157-162, 1992); a pH regulated promoter regulated by aerobic or anaerobic conditions (Tolentino et al.); a pH regulated promoter regulated by combining pH control with anaerobic/aerobic conditions (Tolentino et al.); an arabinose controlled promoter regulated by arabinose levels in culture media (Guzman et al., J. Bacteriol. 177, 4121-4130, 1995); repression of an arabinose controlled promoter with glucose yielding extremely low levels of synthase expression (Guzman et al.); a T7 RNA polymerase promoter such as  $\phi 10$  regulated by T7 RNA polymerase; promoter regions of heat shock genes such as *dnaK*, *grpE*, and *lon*, that can be induced either through heat shock or other environmental stresses such as the addition of chemical inducers such as ethanol (Van Dyk et al., J. Bacteriol. 177, 6001-6004, 1995).

#### Expression Systems

In the preferred embodiment, the host is a bacteria which has been genetically engineered so that it secretes polymer rather than accumulating it in insoluble granules, for example, by genetically engineering the host cell with a gene that allows lysis of the cells when induced. The most preferred host is *E. coli*. Others include Gram positive bacteria such as *Corynebacterium*, *Pseudomonas*, eukaryotic cells, and plant hosts.

Prokaryotic, eukaryotic and plant systems can be created to produce a range of polymers possessing different molecular weights and polydispersities by placing promoters in front of the synthase gene that are inducible to different levels. Alternatively, a series of separate strains, cell lines, or plants containing constitutive promoters of different strengths could be created such that each strain, cell line, or plant produces one polymer product of the desired molecular weight and polydispersity.

In bacterial hosts, synthase activity can be further regulated by employing constitutive or inducible promoters in front of synthase genes in low copy number plasmids, such as those containing the pSC101 replicon, medium copy number plasmids, such as those containing the

-10-

pMB1, p15A, or ColEI replicons, high copy number plasmids, such as the pUC plasmids containing a mutated pMB1 replicon, chromosomal insertion of a single copy of the gene into a host strain, or chromosomal insertion of multiple copies of the gene into a host strain.

5           In plants, expression systems for generating polymers possessing different molecular weights can include the construction of a stably transformed plant containing genes encoding the reductase and thiolase, in which the synthase gene is located behind an inducible promoter, such as the soybean heat-shock promoter Gmgspl7.3. Alternatively, a series of  
10 individual stably transformed plants can be created containing genes encoding the reductase and thiolase and in which the PHA synthase gene(s) are behind constitutive promoters of varying strength such that each plant has a different synthase activity and therefore produces a polymer of different molecular weight. PHA production can be targeted  
15 to the plastids of the plants by fusing a transit peptide, such as the pea chloroplast transit peptide, to the thiolase, reductase, and synthase enzymes, a strategy that has been shown to increase polymer yields in transgenic plants (Nawrath et al., Proc. Natl. Acad. Sci USA 91, 12760-12764, 1994).

#### 20           **Fermentation Conditions**

Fermentation conditions that can be used for producing PHA's in bacteria include batch fermentation and continuous culture. Carbon  
sources for either fermentation can be simple sugars or alkanolic or hydroxyalkanoic acids supplemented to the culture medium depending on  
25 the type of PHA that is desired and the genetic background of the host production organism. For example, the co-polymer of 3-hydroxybutyrate and 3-hydroxyvalerate can be formed in *E. coli* by adding propionic acid to the culture medium of an *atoC fadR* mutant strain (Rhie and Dennis, Applied and Environmental Microbiology, 1995, 61, 2487-2492).

30           The data presented in the examples led to the identification of PHA synthase as the component responsible for controlling the molecular weight of PHA biosynthesized in genetically recombinant bacteria such as

*E. coli*. Two constructs were examined, DH5 $\alpha$ /pAeT41, containing the native *A. eutrophus* PHA biosynthetic operon, and DH5 $\alpha$ /pSP2, containing a modified operon in which the ribosome binding site in front of the synthase has been optimized and the transcription of the PHA biosynthetic genes is under the control of an inducible promoter. The role of the synthase in determining the molecular weight of the polymer is most evident upon comparison of the fermentations of DH5 $\alpha$ /pAeT41 and DH5 $\alpha$ /pSP2, induced with 0.4 mM IPTG. Synthase activity, both soluble and insoluble, remains at a constant undetectable level throughout the fermentation of DH5 $\alpha$ /pAeT41, yielding high molecular weight polymer of approximately constant size at the beginning ( $4.3 \times 10^6$  Da) and end ( $4.0 \times 10^6$  Da) of the fermentation. In contrast, an increase in insoluble synthase activity in DH5 $\alpha$ /pSP2 (0.4 mM IPTG) is observed coincident with a decrease in polymer size, yielding polymer of significantly smaller size at the end of the fermentation ( $1.3 \times 10^6$  Da) than at the beginning ( $2.2 \times 10^6$  Da). Approximately equal levels of thiolase activity and little or no reductase activity are observed in both fermentations indicating that these enzymes are not responsible for the observed difference in molecular weight. The role of the synthase is further substantiated in the fermentation of DH5 $\alpha$ /pSP2 induced with 5 mM IPTG in which *in vivo* synthase activities are further increased, yielding polymer of still lower molecular weight ( $7.3 \times 10^5$  Da) at the end of the fermentation.


Although the described methodology for controlling molecular weight *in vivo* is illustrated with a genetically engineered strain of *E. coli* and PHB, it is not limited to *E. coli* or PHB and can be used in any organism expressing either native or genetically engineered PHA biosynthetic genes to produce any member of the class of polymers encompassed by polyhydroxyalkanoates. The control of PHA synthase activity is not limited to induction of an inducible promoter with IPTG, for any method capable of altering the *in vivo* concentration of PHA synthase activity is capable of controlling the molecular weight of polymer produced in the respective organism.

The present invention will be further understood by reference to the following non-limiting examples.

### Example 1: Production and Characterization of PHB Produced in *E. coli*.

5 Methods and Materials:

Fermentation of *E. coli* DH5 $\alpha$ /pAeT41 was used to establish a reference from which to compare all other genetically engineered *E. coli* PHB producers. Plasmid pAeT41, described in U.S. Patent No. 5,245,023 to Peoples, et al., contains a 5 kb genetic fragment encoding the native, unmodified PHA biosynthetic operon from *A. eutrophus* inserted into pUC18. Sequence Listing ID No. 1. pAeT41 (7.7 kb) is shown schematically as:



As with all other plasmids described in this study, plasmid pAeT41 was transformed into the *E. coli* strain DH5 $\alpha$  for polyester production. Strains were cultured at 30°C in a 15 L MCS-10 Bioreactor AG fermentor (MBR, Switzerland) in LB media (LB media contains per L, 10 g tryptone, 5 g yeast extract, and 10 g NaCl) supplemented with glucose (20 g/L) and ampicillin (50 mg/mL). As with all other fermentations in this study, aliquots of cells were removed for enzyme activity analysis at time points throughout the fermentation, pelleted by centrifugation, and frozen at -70°C. Samples were thawed, resuspended in M9 salts (M9 salts contain, per L, 6 g Na<sub>2</sub>HPO<sub>4</sub>, 3 g KH<sub>2</sub>PO<sub>4</sub>, 0.5 g NaCl, and 1 g NH<sub>4</sub>Cl), and divided into three individual samples for the assay of synthase, thiolase, and reductase activity. Cells were isolated by centrifugation, resuspended in lysis buffer, and disrupted by sonication using an Ultrasonic Processor xL (Farmingdale, NY). After lysis, samples were centrifuged at 4°C for 15 min to isolate soluble protein fractions.

-13-

PHA synthase was assayed by monitoring coenzymeA release using 5, 5'-dithiobis(2-nitrobenzoic acid) as described by Gerngross et al. Biochemistry, 1994, 33, 9311-9320. Both the soluble protein fraction and the crude sonicated lysate were assayed, allowing the determination of both soluble and insoluble synthase enzyme activities. Prior to sonication, samples for the assay of PHA synthase were resuspended in 50 mM  $\text{KH}_2\text{PO}_4$  (pH 7.0) containing 5% glycerol. AcetoacetylCoA reductase was assayed by monitoring the oxidation of NADPH as described by Ploux, et al., Eur. J. Biochem. 1988, 174, 177-182, with the exception that the acetoacetylCoA concentration was increased to 1.8 mM. Prior to sonication, samples for the assay of reductase activity were resuspended in 10 mM Tris-Cl (pH 8.0), 1 mM EDTA, 10 mM  $\beta$ -mercaptoethanol, 20% glycerol, and 0.2 mM phenylmethylsulfonyl fluoride.  $\beta$ -ketothiolase activity was assayed by measuring the rate of  $\text{NAD}^+$  formation as described by Nishimura et al., Arch. Microbiol. 1978, 116, 21-27. Prior to sonication, samples for the assay of thiolase activity were resuspended in 10 mM Tris-Cl (pH 7.3) containing 5 mM  $\beta$ -mercaptoethanol. The PHB content in fermentation broths was assayed as described by Law and Slepecky, J. Bacteriol. 1961, 82, 33-36. The glucose concentration in fermentation broths was determined using a 1050 Hewlett Packard HPLC system equipped with a model 1047A refractive index detector and a Bio-Rad Aminex HPX-87H column maintained at 40°C. Glucose was eluted with a mobile phase of 0.008N sulfuric acid at a flow rate of 0.6 mL/min.

During batch fermentation of DH5 $\alpha$ /pAeT41 (Figure 1A), the initial 20 g/L of glucose supplied to the cells was completely consumed after 18.7 h. Dry cell weight and PHB concentration reached a maximum of 8.7 and 6.0 g/L after 18.7 and 23.3 h of fermentation, respectively. Despite localization of the *A. eutrophus* PHA biosynthetic operon on the high copy plasmid pUC18, no soluble PHA synthase activity was detected during the entire DH5 $\alpha$ /pAeT41 fermentation (Figure 2). The presence of polymer in cell lysates often results in localization of synthase activity

-14-

in the insoluble portion of the lysate (Fukui et al., Microbiol. 1976, 110, 149-156.; Haywood et al., FEMS Microbiology Letters, 1989, 57, 1-6). An additional assay was thus performed for all fermentation samples by measuring the combined soluble and insoluble fractions in the crude lysate prior to centrifugation. DH5 $\alpha$ /pAeT41 lysates assayed in this way still contained no detectable synthase activity (Figure 3A). Maximum reductase activity of 0.033 U/mg was observed at 18.7 h (Figure 4) while assays for thiolase activity yielded a maximum of 2.5 U/mg at the 14.6 h (Figure 5).

10 Polymer purification from samples for molecular weight analysis proceeded as follows. Cells were pelleted by centrifugation and washed with distilled water. Cells were collected by centrifugation, lyophilized, and refluxed in chloroform for 5 h. The cellular debris was removed from the polymer solution by filtration through a sintered glass funnel.

15 PHB was precipitated from the chloroform solution with one volume of hexane, isolated by filtration through a sintered glass funnel, and dried overnight *in vacuo*. <sup>1</sup>H NMR analysis of the polymer dissolved in CDCl<sub>3</sub> confirmed that the isolated material was PHB in high purity [<sup>1</sup>H NMR (CDCl<sub>3</sub>; 300 MHz)  $\delta$ =1.24(d,  $\xi$ =6.3Hz, 3H), 2.44 (dd,  $\xi$ =6.5, 15.5 Hz, 20 1H), 2.58 (dd,  $\xi$ =7.4, 15.5, 1 H), 5.23 (m, 1H)].

Gel permeation chromatography without light scattering (Figures 6B and 6C) was performed on a Progel-TSK G7000H<sub>XL</sub> column in series with a Shodex K-805 GPC column. Polymer samples were eluted in chloroform at 1 mL/min at 30°C.

25 The weight average molecular weight ( $M_w$ ) and Polydispersity index (PDI), equivalent to  $M_w/M_n$  where  $M_n$  is the number average molecular weight, were measured for each polymer sample by multi-angle light scattering. Light scattering was performed using a Waters model 501 pump and model 410 differential refractometer equipped with a

30 Shodex K-807LC GPC column and a Dawn-F multi-angle laser photometer (Wyatt Technology). Polymer samples were eluted with 2,2,2-trifluoroethanol at 35°C. Polymethylmethacrylate standards were



-15-

used to normalize the instrument and light scattering analysis of the standards yielded molecular weight values in good agreement with those reported by the supplier.

Polymer samples isolated at various time points from the fermentation of DH5 $\alpha$ /pAeT41 possessed  $M_w$  ranging from  $4.3 \times 10^6$  to  $4.0 \times 10^6$  Da with the exception of a small drop to  $3.1 \times 10^6$  Da at the 23 h time point (Figure 3B),  $M_w$  values that are significantly larger than the  $1.0 \times 10^6$  to  $1.2 \times 10^6$  Da  $M_w$  observed for polyester isolated from routine fermentations of *A. eutrophus* (Kawaguchi and Doi, Macromolecules 1992, 25, 2324-2329.; Hahn et al., Biotechnology and Bioengineering, 1994, 44, 256-261). The polydispersity index ranged from 1.01 to 1.08 during the fermentation, (Figure 6) signifying a polymer product with a much narrow molecular weight distribution than the polymer possessing a PDI of 2.0 isolated from *A. eutrophus* by Kawaguchi and Doi (1992).

**Example 2: Increasing PHA synthase activity and effect on PHB mw.**

Since little or no PHA synthase activity is detected in either the soluble or insoluble fractions of DH5 $\alpha$ /pAeT41 lysates, a new construct was designed to test the effect of elevated synthase activity on the molecular weight of PHB. An *E. coli* ribosome binding site was inserted into the plasmid in place of the *A. eutrophus* synthase ribosome binding site to increase synthase activity in the presence of genes encoding  $\beta$ -ketothiolase and acetoacetylCoA reductase. Plasmid pSP2 was constructed containing the strong inducible *trc* promoter, a gene encoding PHA synthase with an optimal *E. coli* ribosome binding site, and genes encoding the thiolase and reductase. A 2.3 kb fragment encoding  $\beta$ -ketothiolase (PhaA) and acetoacetyl-CoA reductase (PhaB) was isolated from plasmid pAeT10 (Peoples and Sinskey, 1989b) upon digestion with *Pst* I (Figures 7A-B). The fragment was ligated into the 4.2 kb vector pTRCN (Gerngross et al., 1994) that has been previously digested with *Pst* I and calf intestinal alkaline phosphatase. A plasmid containing *phaA*

-16-

adjacent to the *trc* promoter of plasmid pTRCN was isolated and named pSP1A. A 1.7 kb fragment encoding PHA synthase (PhaC) was isolated from plasmid pKAS4 (Gerngross et al., 1994) upon digesting the plasmid with *EcoR* I and *BamH* I. The fragment was ligated into pSP1A that had  
5 been previously digested with *EcoR* I and *BamH* I. A 8.2 kb plasmid containing *phaC* behind the *trc* promoter, followed by a fragment containing *phaA* and *phaB*, was isolated and named pSP2 (Figure 7B). The presence of a plasmid-borne *lacI<sup>q</sup>* gene on pSP2 allows the transcription of all three PHA biosynthetic genes in this synthetic operon  
10 to be tightly controlled by the amount of IPTG added to the culture medium.

Initial batch fermentation of DH5 $\alpha$ /pSP2 was performed in the presence of 0.4 mM IPTG which was added to the culture once the absorbance at 600 nm reached 0.6. DH5 $\alpha$ /pSP2 induced in this manner  
15 consumed all glucose after 18.3 h of fermentation (Figure 1B). Dry cell weight and PHB content were found to be 10.4 and 7.9 g/L at 18.3 and 35.5 h, respectively. A  $M_w$  of  $2.2 \times 10^6$  Da was detected after 6.9 h of fermentation and  $M_w$  values steadily decreased until 35.5 h at which time isolated polymer possessed a  $M_w$  of  $1.3 \times 10^6$ , three fold smaller than the  
20  $4.0 \times 10^6$  Da observed at the end of the DH5 $\alpha$ /pAeT41 fermentation (Figure 3B). The observed increase in PHB concentration (Figure 1B) during the time span that a decrease in polymer molecular weight was observed (Figure 3B) indicates that the decrease in polymer molecular weight is not due to polymer degradation during the fermentation.

25 Enzyme activities were therefore assayed for the DH5 $\alpha$ /pSP2 (0.4 mM IPTG) fermentation to determine if a difference in enzyme activities coincided with the observed differences in  $M_w$  of polymer isolated from strains DH5 $\alpha$ /pAeT41 and DH5 $\alpha$ /pSP2 (0.4 mM IPTG). The most prominent difference in enzyme activity was the presence of detectable  
30 synthase activity in DH5 $\alpha$ /pSP2 (0.4 mM IPTG), which was predominantly insoluble during the fermentation, yielding a maximum specific activity of 1.4 U/mg in the combined soluble and insoluble

-17-

fractions at 13.3 h (Figure 3A). This observation indicated that the concentration of synthase might play a role in determining the size of the polymer produced in the host cell. Soluble synthase in DH5 $\alpha$ /pSP2 yielded a maximum activity of 0.11 U/mg at 18.3 h (Figure 2). No reductase activity was detected in the fermentation (Figure 4) and assays for thiolase activity yielded a maximum of 3.6 U/mg at 11.5 h time point of the fermentation (Figure 5). The polymer isolated from the DH5 $\alpha$ /pSP2 (0.4 mM IPTG) fermentation possessed a broader molecular weight distribution than polymer isolated from DH5 $\alpha$ /pAeT41 as seen from the increase in polydispersity index values which reached a maximum of 1.57 (Figure 6).

To further demonstrate the ability of PHA synthase to regulate the size of PHA produced in a host cell, the transcription of PHA biosynthetic genes in DH5 $\alpha$ /pSP2 was elevated by increasing the concentration of the inducing agent, IPTG, to 5 mM. Maximum soluble synthase activity increased from the 0.11 U/mg observed in DH5 $\alpha$ /pSP2 induced with 0.4 mM IPTG to 0.21 U/mg when induced with 5 mM IPTG (Figure 2). Likewise, insoluble synthase activity increased, yielding 2.5 U/mg at 16.5 h (Figure 3A). A further reduction of size in the isolated polymer was observed, yielding  $M_w$  values of  $2.2 \times 10^6$  Da after 5.8 h of fermentation which decreased to  $7.8 \times 10^5$  Da at 30.2 h, a value five fold smaller than the  $4.0 \times 10^6$  Da observed at the end of the DH5 $\alpha$ /pAeT41 fermentation (Figure 3B).

No reductase activity was detected during the fermentation (Figure 4) and thiolase activity yielded a maximum activity of 12.3 U/mg at 16.5 h (Figure 5). Fermentation parameters were comparable to those measured for DH5 $\alpha$ /pSP2 induced with 0.4 mM IPTG with dry cell weight and PHB concentration maximum yields of 9.5 and 7.6 g/L, respectively, at 30.2 h (Figure 1C). All glucose was consumed from the fermentation at 16.5 h.

**Example 3: Effect of synthase activity on molecular weight distribution.**

Analysis of the results in Example 1 by GPC in line with light-scattering showed that the polydispersity index of polymer isolated from  
5 DH5 $\alpha$ /pSP2 induced with 5 mM IPTG was 2.8 at 25.4 h, indicating a broader molecular weight distribution than polymer samples isolated from DH5 $\alpha$ /pAet41 and DH5 $\alpha$ /pSP2 induced with 0.4 mM IPTG (Figure 6A).

The control of molecular weight distribution is reflected by the different polydispersity indices measured for polymer samples isolated  
10 from strains DH5 $\alpha$ /pAet41, DH5 $\alpha$ /pSP2 induced with 0.4 mM IPTG, and DH5 $\alpha$ /pSP2 induced with 5 mM IPTG (Figure 6A). The broadening of distributions upon induction of DH5 $\alpha$ /pSP2 with IPTG can be attributed to increasing the concentration of PHA synthase midway through the fermentation. The basal levels of synthase activity before  
15 IPTG induction, due to incomplete repression of the trc promoter by the lacI<sup>q</sup> gene product, produce a small pool of polymers with high molecular weights. Induction with IPTG midway through the fermentation increases the number of polymer chains competing for substrate producing a new pool of polymers with a shorter chain length. Since the polymer pool  
20 now encompasses long chains manufactured before IPTG induction and new shorter chains produced after IPTG induction, the molecular weight distribution of the final polymer product broadens. The extent of synthase induction midway through the fermentation determines the final distribution of the polymer product. This is most evident upon  
25 examination of the GPC chromatograms of DH5 $\alpha$ /pSP2 induced with 0.4 mM IPTG (Figure 6B) and DH5 $\alpha$ /pSP2 induced with 5 mM IPTG (Figure 6C). The chromatograms of both strains reveal the production of a polymer whose median molecular weight exceeds 10<sup>6</sup> Da at an early time point of the fermentation (DH5 $\alpha$ /pSP2, 0.4 mM IPTG, 6.9 h;  
30 DH5 $\alpha$ /pSP2, 5 mM IPTG, 5.8 h). However, upon induction of DH5 $\alpha$ /pSP2 with either 0.4 mM or 5 mM IPTG midway through the fermentation, the median molecular weight of polymer isolated from

-19-

- DH5 $\alpha$ /pSP2 induced with 5 mM IPTG (23.4 h) shifts to a lower value than polymer isolated from DH5 $\alpha$ /pSP2 induced with 0.4 mM IPTG (18.3 h) yielding a broader molecular weight distribution for the 5 mM sample. Accordingly, varying the extent and time of induction of PHA synthase in
- 5 a genetic recombinant production strain can be used to produce polymer products with different molecular weight distributions.

-20-

## SEQUENCE LISTING

- (1) GENERAL INFORMATION:
- (i) APPLICANT: Massachusetts Institute of Technology
  - (ii) TITLE OF INVENTION: Method for Controlling Molecular Weight of Polyhydroxyalkanoates
  - (iii) NUMBER OF SEQUENCES: 1
  - (iv) CORRESPONDENCE ADDRESS:
    - (A) ADDRESSEE: Patrea L. Pabst
    - (B) STREET: 2800 One Atlantic Center, 1201 West Peachtree Street
    - (C) CITY: Atlanta
    - (D) STATE: Georgia
    - (E) COUNTRY: USA
    - (F) ZIP: 30309
  - (v) COMPUTER READABLE FORM:
    - (A) MEDIUM TYPE: Floppy disk
    - (B) COMPUTER: IBM PC compatible
    - (C) OPERATING SYSTEM: PC-DOS/MS-DOS
    - (D) SOFTWARE: PatentIn Release #1.0, Version #1.25
  - (vi) CURRENT APPLICATION DATA:
    - (A) APPLICATION NUMBER:
    - (B) FILING DATE: 25 July 1997
    - (C) CLASSIFICATION:
  - (vii) PRIOR APPLICATION DATA:
    - (A) APPLICATION NUMBER: U.S. 08/687,806
    - (B) FILING DATE: 26-JUL-1996
    - (C) CLASSIFICATION:
  - (viii) ATTORNEY/AGENT INFORMATION:
    - (A) NAME: Pabst, Patrea L.
    - (B) REGISTRATION NUMBER: 31,284
    - (C) REFERENCE/DOCKET NUMBER: MIT 6867
  - (ix) TELECOMMUNICATION INFORMATION:
    - (A) TELEPHONE: 404-873-8794
    - (B) TELEFAX: 404-873-8795
- (2) INFORMATION FOR SEQ ID NO:1:
- (i) SEQUENCE CHARACTERISTICS:
    - (A) LENGTH: 4984 base pairs
    - (B) TYPE: nucleic acid
    - (C) STRANDEDNESS: double
    - (D) TOPOLOGY: linear
  - (ii) MOLECULE TYPE: DNA
  - (xi) SEQUENCE DESCRIPTION: SEQ ID NO:1:

```

CCCCGGCAAG TACCTTGCCG ACATCTATGC GCTGGCGCGC ACGCGCCTGG CGCGCGCCGG      60
CTGTACCGAG GTCTACGGCG GCGACGCTG CACCGTGGCC GACGCCGGTC GCTTCTACTC      120
CTATCGGCGC GATGGCGTGA CCGGCCGCAT GGCCAGCCTG GTCTGGCTGG CGGACTGAGC      180
CCGCCGCTGC CTCACTCGTC CTTGCCCTG GCGCCTGCGC CGCGCTCGGC TTCAGCCTTG      240
CGTCGGCGGC GGCCGGGCGT GCCCATGATG TAGAGCACCA CGCCACCGGC GCCATGCCAT      300
ACATCAGGAA GGTGGCAACG CCTGCCACCA CGTTGTGCTC GGTGATCGCC ATCATCAGCG      360
CCACGTAGAG CCAGCCAATG GCCACGATGT ACATCAAAAA TTCATCCTTC TCGCCTATGC      420
TCTGGGGCCT CGGCAGATGC GAGCGCTGCA TACCGTCCGG TAGGTCGGGA AGCGTGCAGT      480
GCCGAGGCGG ATTCCCGCAT TGACAGCGCG TCGGTTGCAA GGCAACAATG GACTCAAATG      540
TCTCGGAATC GCTGACGATT CCCAGGTTTC TCCGGCAAGC ATAGCGCATG GCGTCTCCAT      600
GCGAGAATGT CGCGCTTGCC GGATAAAGG GGAGCCGCTA TCGGAATGGA CGCAAGCCAC      660
GGCCGCAGCA GGTGCGGTCG AGGGCTTCCA GCCAGTTCCA GGGCAGATGT GCCGGCAGAC      720

```

-21-

CCTCCCGCTT TGGGGGAGGC GCAAGCCGGG TCCATTTCGA TAGCATCTCC CCATGCAAAG	780
TGCCGGCCAG GGCAATGCCC GGAGCCGGTT CGAATAGTGA CGGCAGAGAG ACAATCAAAT	840
CATGGCGACC GGCAAAGGCG CGGCAGCTTC CACGCAGGAA GGCAAGTCCC AACCATTCAA	900
GGTCACGCCG GGGCCATTTC ATCCAGCCAC ATGGCTGGAA TGGTCCCGCC AGTGGCAGGG	960
CACTGAAGGC AACGGCCACG CGGCCGCGTC CGGCATTCCG GGCCTGGATG CGCTGGCAGG	1020
CGTCAAGATC GCGCCGCGC AGCTGGGTGA TATCCAGCAG CGCTACATGA AGGACTTCTC	1080
AGCGCTGTGG CAGGCCATGG CCGAGGGCAA GGCCGAGGCC ACCGGTCCGC TGCACGACCG	1140
GCGCTTCGCC GCGCAGCAT GGCACACAA CCTCCCATAT CGCTTCGCTG CCGCGTTCTA	1200
CCTGCTCAAT GCGCGCGCCT TGACCGAGCT GGCCGATGCC GTCGAGGCCG ATGCCAAGAC	1260
CCGCCAGCGC ATCCGCTTCG CGATCTCGCA ATGGGTGCAT GCGATGTCGC CCGCCAACCT	1320
CCTTGCCACC AATCCCGAGG CGCAGCGCCT GCTGATCGAG TCGGGCGGCG AATCGCTGCG	1380
TGCCGGCGTG CGCAACATGA TGGAAGACCT GACACGCGGC AAGATCTCGC AGACCGACGA	1440
GAGCGCGTTT GAGGTTCGGC GCAATGTCGC GGTGACCGAA GGCGCCGTGG TCTTCGAGAA	1500
CGAGTACTTC CAGCTGTTGC AGTACAAGCC GCTGACCGAC AAGGTGCACG CGCGCCCGCT	1560
GCTGCGGGTG CCGCCGTGCA TCAACAAGTA CTACATCCTG GACCTGCAGC CGGAGAGCTC	1620
GCTGCTGCGC CATGTGGTGG AGCAGGGACA TACGGTGTTC CTGGTGTCTG GGCGAATCC	1680
GGACGCCAGC ATGGCCGGCA GCACCTGGGA CGACTACATC GAGCACGCGG CCATCCGCGC	1740
CATCGAAGTC GCGCGCGACA TCAGCGGCCA GGACAAGATC AACGTGCTCG GCTTCTGCGT	1800
GGGCGGCACC ATTGTCTCGA CCGCGCTGGC GGTGCTGGCC GCGCGCGGCG AGCACCCGGC	1860
CGCCAGCGTC ACGCTGCTGA CCACGCTGCT GGACTTTGCC GACACGGGCA TCCTCGACGT	1920
CTTTGTGAC GAGGGCCATG TGCAGTTGCG CGAGGCCACG CTGGGCGGCG GCGCCGGCGC	1980
GCCGTGCGCG CTGCTGCGCG GCCTTGAGCT GGCCAATACC TTCTCGTTCT TGCGCCCGAA	2040
CGACCTGGTG TGGAACACG TGGTCGACAA CTACCTGAAG GGCAACACGC CGGTGCCGTT	2100
CGACCTGCTG TTCTGGAACG GCGACGCCAC CAACCTGCCG GGGCCGTGGT ACTGCTGGTA	2160
CCTGCGCCAC ACCTACCTGC AGAACGAGCT CAAGGTACCG GGCAAGCTGA CCGTGTGCGG	2220
CGTGCCGGTG GACCTGGCCA GCATCGACGT GCCGACCTAT ATCTACGGCT CGCGCGAAGA	2280
CCATATCGTG CCGTGGACCG CGGCCTATGC CTCGACCGCG CTGCTGGCGA ACAAGCTGCG	2340
CTTCGTGCTG GGTGCGTCGG GCCATATCGC CGGTGTGATC AACCCGCCG CCAAGAACAA	2400
GCGCAGCCAC TGGACTAACG ATGCGCTGCC GGAGTCGCCG CAGCAATGGC TGGCCGGCGC	2460
CATCGAGCAT CACGGCAGCT GGTGGCCGGA CTGGACCGCA TGGCTGGCCG GGCAGGCCGG	2520
CGCGAAACGC GCCGCGCCCG CCAACTATGG CAATGCGCGC TATCGCGCAA TCGAACCCGC	2580
GCCTGGGCGA TACGTCAAAG CCAAGGCATG ACGCTTGCAAT GAGTGCCGGC GTGCGTCATG	2640
CACGGCGCCG GCAGGCCTGC AGGTTCCCTC CCGTTTCCAT TGAAAGGACT ACACAATGAC	2700
TGACGTTGTC ATCGTATCCG CCGCCCGCAC CGCGGTGCGC AAGTTTGCGG GCTCGCTGGC	2760

-22-

CAAGATCCCG	GCACCGGAAC	TGGGTGCCGT	GGTCATCAAG	GCCGCGCTGG	AGCGCGCCGG	2820
CGTCAAGCCG	GAGCAGGTGA	GCGAAGTCAT	CATGGGCCAG	GTGCTGACCG	CCGGTTCGGG	2880
CCAGAACCCC	GCACGCCAGG	CCGCGATCAA	GGCCGGCCTG	CCGGCGATGG	TGCCGGCCAT	2940
GACCATCAAC	AAGGTGTGCG	GCTCGGGCCT	GAAGGCCGTG	ATGCTGGCCG	CCAACGCGAT	3000
CATGGCGGGC	GACGCCGAGA	TCGTGGTGGC	CGGCGGCCAG	GAAAACATGA	GCGCCGCCCC	3060
GCACGTGCTG	CCGGGCTCGC	GCGATGGTTT	CCGCATGGGC	GATGCCAAGC	TGGTCGACAC	3120
CATGATCGTC	GACGGCCTGT	GGGACGTGTA	CAACCAGTAC	CACATGGGCA	TCACCGCCGA	3180
GAACGTGGCC	AAGGAATACG	GCATCACACG	CGAGGCGCAG	GATGAGTTCG	CCGTCGGCTC	3240
GCAGAACAAAG	GCCGAAGCCG	CGCAGAAGGC	CGGCAAGTTT	GACGAAGAGA	TCGTCCCGGT	3300
GCTGATCCCG	CAGCGCAAGG	GCGACCCGGT	GGCCTTCAAG	ACCGACGAGT	TCGTGCGCCA	3360
GGGCGCCACG	CTGGACAGCA	TGTCCGGCCT	CAAGCCCGCC	TTCGACAAGG	CCGGCACGGT	3420
GACCGCGGCC	AACGCCTCGG	GCCTGAACGA	CGGCGCCGCC	GCGGTGGTGG	TGATGTCGGC	3480
GGCCAAGGCC	AAGGAACTGG	GCCTGACCCC	GCTGGCCACG	ATCAAGAGCT	ATGCCAACGC	3540
CGGTGTGCGT	CCCAAGGTGA	TGGGCATGGG	CCCGGTGCCG	GCCTCCAAGC	GCGCCCTGTC	3600
GCGCGCCGAG	TGGACCCCGC	AAGACCTGGA	CCTGATGGAG	ATCAACGAGG	CCTTTGCCGC	3660
GCAGGCGCTG	GCGGTGCACC	AGCAGATGGG	CTGGGACACC	TCCAAGGTCA	ATGTGAACGG	3720
CGGCGCCATC	GCCATCGGCC	ACCCGATCGG	CGCGTCGGGC	TGCCGTATCC	TGGTGACGCT	3780
GCTGCACGAG	ATGAAGCGCC	GTGACGCGAA	GAAGGGCCTG	GCCTCGCTGT	GCATCGGCGG	3840
CGGCATGGGC	GTGGCGCTGG	CAGTCGAGCG	CAAATAAGGA	AGGGGTTTTT	CGGGGCCGCG	3900
CGCGGTGGC	GCGGACCCGG	CGACGATAAC	GAAGCCAATC	AAGGAGTGGA	CATGACTCAG	3960
CGCATTGCGT	ATGTGACCGG	CGGCATGGGT	GGTATCGGAA	CCGCCATTTG	CCAGCGGCTG	4020
GCCAAGGATG	GCTTTCGTGT	GGTGGCCGGT	TGCGGCCCCA	ACTCGCCGCG	CCGCGAAAAG	4080
TGGCTGGAGC	AGCAGAAGGC	CCTGGGCTTC	GATTTTCATTG	CCTCGGAAGG	CAATGTGGCT	4140
GACTGGGACT	CGACCAAGAC	CGCATTGAC	AAGGTCAAGT	CCGAGGTCGG	CGAGGTTGAT	4200
GTGCTGATCA	ACAACGCCGG	TATCACCCGC	GACGTGGTGT	TCCGCAAGAT	GACCCGCGCC	4260
GACTGGGATG	CGGTGATCGA	CACCAACCTG	ACCTCGCTGT	TCAACGTCAC	CAAGCAGGTG	4320
ATCGACGGCA	TGGCCGACCG	TGGCTGGGGC	CGCATCGTCA	ACATCTCGTC	GGTGAACGGG	4380
CAGAAGGGCC	AGTTCGGCCA	GACCAACTAC	TCCACCGCCA	AGGCCGCCCT	GCATGGCTTC	4440
ACCATGGCAC	TGGCGCAGGA	AGTGGCGACC	AAGGGCGTGA	CCGTCAACAC	GGTCTCTCCG	4500
GGCTATATCG	CCACCGACAT	GGTCAAGGCG	ATCCGCCAGG	ACGTGCTCGA	CAAGATCGTC	4560
GCGACGATCC	CGGTCAAGCG	CCTGGGCCTG	CCGGAAGAGA	TCGCTCGAT	CTGCGCCTGG	4620
TTGTGCTCGG	AGGAGTCCGG	TTTCTCGACC	GGCGCCGACT	TCTCGCTCAA	CGGCGGCCTG	4680
CATATGGGCT	GACCTGCCGG	CCTGGTTCAA	CCAGTCGGCA	GCCGGCGCTG	GCGCCCGCGT	4740
ATTGCGGTGC	AGCCAGCGCG	GCGCACAAGG	CGGCGGGCGT	TTCGTTTCGC	CGCCCGTTTC	4800



-23-

GCGGGCCGTC	AAGGCCCGCG	AATCGTTTCT	GCCCGCGCGG	CATTCCTCGC	TTTTTGCGCC	4860
AATTCACCGG	GTTTTCCTTA	AGCCCCGTCG	CTTTTCTTAG	TGCCTTGTTG	GGCATAGAAT	4920
CAGGGCAGCG	GCGCAGCCAG	CACCATGTTC	GTGCAGCGCG	GCCCTCGCGG	GGGCGAGGCT	4980
GCAG						4984

We claim:

1. A method for controlling molecular weight and dispersity of polyhydroxyalkanoates comprising  
controlling the amount of polyhydroxyalkanoate synthase activity in a host expressing the synthase and providing substrate for polymerization of polyhydroxyalkanoates, wherein the molecular weight of the polyhydroxyalkanoate is inversely proportional to the activity of the polyhydroxyalkanoate synthase activity.
2. The method of claim 1 wherein the amount of synthase activity is controlled by engineering the gene encoding the synthase to be under the control of an inducible promoter and regulating the expression of the synthase by inducing the promoter.
3. The method of claim 1 wherein the activity of the synthase is altered over time to increase the molecular weight dispersity of the polyhydroxyalkanoate.
4. The method of claim 1 wherein the synthase activity is maintained at substantially the same specific activity over a period of time to yield a polyhydroxyalkanoate having a molecular weight dispersity of between 1.02 and 2.81.
5. The method of claim 1 wherein the polyhydroxyalkanoate has a molecular weight range of between 700,000 and 4,000,000 g/mol.
6. The method of claim 1 wherein the amount of synthase activity is controlled by increasing the activity of the synthase.
7. An expression system for the synthesis of polyhydroxyalkanoate comprising a synthase under the control of an inducible promoter.
8. The expression system of claim 7 comprising a host selected from the group consisting of plants and bacteria expressing a reductase and thiolase.
9. A polyhydroxyalkanoate composition having a molecular weight dispersity of between 1.02 and 2.81.

-25-

10. The polyhydroxyalkanoate composition of claim 9 wherein the polyhydroxyalkanoate has a molecular weight range of between 700,000 and 4,000,000 g/mol.

1/8




FIG. 1a




FIG. 1b

SUBSTITUTE SHEET (RULE 26)

2/8




FIG. 1c




FIG. 2

SUBSTITUTE SHEET (RULE 26)

3/8




FIG. 3a




FIG. 3b

SUBSTITUTE SHEET (RULE 26)

4/8




FIG. 4




FIG. 5

SUBSTITUTE SHEET (RULE 26)




FIG. 6a

SUBSTITUTE SHEET (RULE 26)



6/8




FIG. 6b





FIG. 6c

SUBSTITUTE SHEET (RULE 26)

7/8


FIG. 7a



SUBSTITUTE SHEET (RULE 26)

8/8

FIG. 7b



SUBSTITUTE SHEET (RULE 26)

# INTERNATIONAL SEARCH REPORT

Internat Application No  
PCT/US 97/13301

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 6 C12N15/52 C12P7/62 C12N9/00 //C12N1/21,C12N5/14

According to International Patent Classification(IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 C12P C12N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 95 21257 A (INNOVATIVE TECH CENTER) 10 August 1995 see page 11; claims ---	1
A	WO 95 21260 A (INNOVATIVE TECH CENTER) 10 August 1995 see page 11; claims ---	1
A	WO 96 05316 A (MASSACHUSETTS INST TECHNOLOGY ;METABOLIX INC (US)) 22 February 1996 see claims ---	1
A	WO 91 00917 A (MASSACHUSETTS INST TECHNOLOGY) 24 January 1991 see claims ---	1
	-/--	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex

**\* Special categories of cited documents**

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

1 December 1997

Date of mailing of the international search report

19/12/1997

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel: (+31-70) 340-2040, Tx 31 651 epo nl.  
Fax: (+31-70) 340-3016

Authorized officer

Delanghe, L

# INTERNATIONAL SEARCH REPORT

Internet	Application No
PCT/US 97/13301	

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 44 17 169 A (VOGELBUSCH GMBH) 23 November 1995 see claims ---	1
A	WO 89 00202 A (MASSACHUSETTS INST TECHNOLOGY) 12 January 1989 see the whole document ---	1
A	CHEMICAL ABSTRACTS, vol. 124, no. 5, 29 January 1996 Columbus, Ohio, US; abstract no. 50315, KOIZUMI, FUMITAKE ET AL: "Molecular weight of poly(3-hydroxybutyrate) during biological polymerization in Alcaligenes eutrophus" XP002048625 see abstract & PLAST. ENG. (N. Y.) (1995), 29(DEGRADABLE POLYMERS, RECYCLING, AND PLASTICS WASTE MANAGEMENT), 167-82 CODEN: PLENEZ:ISSN: 1040-2527, ---	1
P,X	CHEMICAL ABSTRACTS, vol. 126, no. 7, 17 February 1997 Columbus, Ohio, US; abstract no. 86943, SIM, SANG JUN ET AL: "PHA synthase activity controls the molecular weight and polydispersity of polyhydroxybutyrate in vivo" XP002048626 see abstract & NAT. BIOTECHNOL. (1997), 15(1), 63-67 CODEN: NABIF9;ISSN: 1087-0156, -----	1-10

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Internat Application No

PCT/US 97/13301

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9521257 A	10-08-95	EP 0742828 A	20-11-96
WO 9521260 A	10-08-95	EP 0742832 A	20-11-96
WO 9605316 A	22-02-96	US 5480794 A	02-01-96
		AU 3322195 A	07-03-96
WO 9100917 A	24-01-91	CA 2062816 A	11-01-91
		EP 0482077 A	29-04-92
		JP 5500751 T	18-02-93
		US 5480794 A	02-01-96
		US 5534432 A	09-07-96
		US 5663063 A	02-09-97
		US 5245023 A	14-09-93
		US 5250430 A	05-10-93
DE 4417169 A	23-11-95	NONE	
WO 8900202 A	12-01-89	EP 0329770 A	30-08-89
		EP 0688865 A	27-12-95
		US 5480794 A	02-01-96
		US 5512669 A	30-04-96
		US 5534432 A	09-07-96
		US 5661026 A	26-08-97
		US 5663063 A	02-09-97
		US 5229279 A	20-07-93
		US 5245023 A	14-09-93
		US 5250430 A	05-10-93